

FIBRANGyps NEXT MESH



Product Description

Ranforced mesh produced with glass fiber wire with sizing anti-alkaline, center distance 4 x 4.9 mm and a basis weight equal to 160 gr / m2.

Applications

Suitable for the finishing of FIBRANGyps NEXT BOARD, such as armor layer top coat plaster in order to absorb and distribute the mechanical stresses thus avoiding cracks in the facade.

Features	U. M.	Value	Standard
Dimension of meshes	mm	Warp - 4 Weft - 4,9	-
Width	m	50	-
Length	mm	1000	-
Thickness	mm	0,6	-
Treated fabric weight	g/m ²	Min. 160	-
Loss on ignition (LOI)	%	Min. 18	-
Tensile Strength	N/50 mm	Initial condition Warp / Weft (average) - 2100/1800 Initial condition Warp / Weft (individual) - 2000/1700	-